



ShurTuff®
Durable Mailers

Introducing new ShurTuff® environmentally friendly durable mailers, combining advanced technology and recycled resins that set new standards in toughness, strength and sustainability.

Properties		Units	Results	Test Method
Tear	MD	gram	500	ASTM D 1938
	TD	gram	1000	
Impact Strength		lb./lb.-f	2.0	ASTM D 4272
Tensile	MD	psi	2500	ASTM D 882
	TD	psi	2200	

** All test values are "typical" and may vary due to the use of recycled resin. Product recycled resin content will be a minimum of 25% and a maximum of 50%.*



Protective Packaging
301 Mayhill Street
Saddle Brook, NJ 07663-5303
800-648-9093 Fax: 201-712-7070
www.sealedair.com

T-227 Rev. 9/12